

Product information

REV2015204

Stuffing-Box-Packing Type 2236

Material composition

The new TEADIT packing style 2236 is made from layers of flexible graphite tape plied into compact strands; each individual filament is reinforced with an Inconel wire jacket. This yarn is then treated in a special process and then braided to form a dense yet malleable packing, which is subsequently treated with lubricating agents to reduce stem friction and a corrosion inhibitor to prevent pitting. (Inconel is a registered trademark of International Co.) Please note: the colour of the actual product might vary from the above image on this data-sheet.

Properties

TEADIT style 2236 is a special valve packing which assures extremely low emission, especially designed for high pressure and high temperature service. It is self-lubricating, non hardening, dimensionally stable and easy to install. The Inconel wire mesh covering makes this packing highly resistant to extrusion, the advanced construction assures supreme leakage control and highest integrity in service.

Application areas

Typical applications for style 2236 include all the valves where LOW EMISSION is a must. This packing is suitable for VOC and VHAP emission regulations and exceeds TA-Luft requirements.

Application media

Designed for steam applications, Teadit style 2236 can also be used with most chemicals and gases.

Not suitable for

Highly oxidizing agents at high temperature.

Benefits

Certified Low-Leakage Packing; TA-Luft Certificate; high mechanical and thermal stability; chemically inert within pH range 0-14; quick and easy to install; low friction, special lubricating system; corrosion inhibitor.

FIRE-SAFE CERTIFICATE.



Temperature:

	- temp	+ temp	steam:
(°C)	240	455	650

Pressure:

	rotating:	reciprocating:	static:
(bar)			450

pH: 0 - 14 density: 1,6 v: (m/s) < 1

Tests & Approvals

TA-Luft
Fire-Safe (API 607)

Since all properties, specifications and application parameters shown throughout this catalogue are approximate and may be mutually influenced, your specific application should not be undertaken without independent study and evaluation for suitability. All technical data and advice given is based on experiences TEADIT® has made so far. Failure to select proper sealing products can result in damage and/or personal injury. Properties, specifications and application parameters are subject to change without notice. TEADIT® does not undertake any liability of any kind whatsoever. Please note: the colour of the actual product might vary from the above image on this data-sheet.

TEADIT INT. - Rosenheimer Str. 10, 6330 Kufstein, AUSTRIA, Tel.: +43-5372-64020-0, Fax: +43-5372-64020-20, austria@teadit.eu, www.teadit.eu
TEADIT Deutschland - Schanzenstr. 35, 51063 Cologne, GERMANY, Tel.: +49-221-922 342-0, Fax: +49-221-922 342-22, germany@teadit.eu